



## Material Specification Sheet

<b>Lining Code:</b>	SR262 (Color – Tan / Black)
<b>Type:</b>	Chlorobutyl
<b>Use:</b>	Special lining for general chemical service with good resistance to high heat, service temperature up to 250°F.
<b>Tie Gum:</b>	Yes
<b>Cement:</b>	One coat Chemlok 289 on metal One coat Chemlok 290 on metal One coat Chemlok 286 on metal One coat Chemlok 286 on metal or lining
<b>Freshening Solvent:</b>	Xylol or Toluol, use up to 10%
<b>Cure, for thickness up to 1 /4”:</b>	
<b>Pressure Cure (autoclave)</b>	Slowly rise to 250°F (15 psi) Hold 3 hours @ 250°F (15 psi)
<b>Internal Steam Cure:</b>	Slowly rise to 250°F (15 psi) Hold 6 hours @ 250°F (15 psi)
<b>Atmosphere Steam Cure:</b>	24 hour @ 212 °F
<b>Repair Compound:</b>	Same or CC7762
<b>Cured Physical Property:</b>	Hardness 62 ± 5 A  Gravity: 1.21
<b>Test Procedure:</b>	Use Standard 10,000 Volt Spark Tester



salem-republic rubber company  
**1-800-686-4199** · (330)938-9809 fax  
475 West California Avenue · Sebring, Ohio 44672 · USA  
[www.salem-republic.com](http://www.salem-republic.com)