



Material Specification Sheet

Lining Code:	SR262 (Color – Tan / Black)
Type:	Chlorobutyl
Use:	Special lining for general chemical service with good resistance to high heat, service temperature up to 250°F.
Tie Gum:	Yes
Cement:	One coat Chemlok 289 on metal One coat Chemlok 290 on metal One coat Chemlok 286 on metal One coat Chemlok 286 on metal or lining
Freshening Solvent:	Xylol or Toluol, use up to 10%
Cure, for thickness up to 1 /4”:	
Pressure Cure (autoclave)	Slowly rise to 250°F (15 psi) Hold 3 hours @ 250°F (15 psi)
Internal Steam Cure:	Slowly rise to 250°F (15 psi) Hold 6 hours @ 250°F (15 psi)
Atmosphere Steam Cure:	24 hour @ 212 °F
Repair Compound:	Same or CC7762
Cured Physical Property:	Hardness 62 ± 5 A Gravity: 1.21
Test Procedure:	Use Standard 10,000 Volt Spark Tester



salem-republic rubber company
1-800-686-4199 · (330)938-9809 fax
475 West California Avenue · Sebring, Ohio 44672 · USA
www.salem-republic.com